



# Technical Data Sheet – ASTM Standard

## Lundhs Antique

*Lundhs Antique has a unique compound of clear blue/purple crystals on brown background.  
Previous trading name for this material was Labrador Antique.*

Technical Properties	Standard	Mean Values
stone name:		Anorthosite
structure:		coarse grained
texture:		oriented feldspar crystals with lustre
Compressive Strength	ASTM C-170	32,108 PSI
Flexural Strength	ASTM C-880	2,237 PSI
Abrasion Resistance	ASTM C-1353	120 wear index value
Water Absorption	ASTM C-97	0.16 %
Density	ASTM C-97	165.3 lb/ft <sup>2</sup>
Modulus of Rupture	ASTM C-99	2,450 PSI
petrographic composition:		feldspar 85% pyroxene 9% chlorite 3% opaques 3%

\* PSI: Pounds Per Square Inch

\*\* Method: American Society for Testing and Materials  
Source: ABIC Testing Laboratories, Inc.

Box 2051, Stubberud  
N-3255 Larvik, Norway

Telephone: +47 33 12 11 64  
Fax: +47 33 18 23 34  
Email: [info@lundhs.no](mailto:info@lundhs.no)  
[www.lundhs.no](http://www.lundhs.no)